Primary Lithium Battery CP253025

3.0V [Li-MnO₂]

BENEFITS

 High Voltage Response, Stable During Most of the Lifetime of the Application

- Energy Density up to 830Wh/L
- Wide Operating Temperature Range (-40 °C ~+70 °C)

 Low Self-discharge Rate (less than 1% per year after 1 year of storage at +25 C)

Optimized Battery Structure, Full Discharge Capacity

• GB 8897.4-2008、 IEC 60086.4:2014 and RoHS



References Data

Electrical characteristics

Open circuit voltage (at 23±2°C)

Nominal capacity

(At +25°C, battery discharged at continuous current 1mA until voltage reaches cut-o voltage 2.0V. The capacity can vary at di erent temperature, discharge current or cut-o voltage.)

Maximum continuous current

30mA

50mA

-40°C~+70°C

3.10V

220mAh

(At +25°C, 2.0V cut-o , battery discharged for minimum 50% of rated capacity.)

Maximum pulse discharge current

Operating temperature range

(At +25°C, 2.0V cut-o , battery discharged for minimum 50% of rated capacity with max pulse for 3 seconds after 27 seconds break. For more battery capacity, please consult HCB.)

Storage (recommended)	+30°C
(For more severe conditions, consult HCB)	75%RH

MAIN APPLICATIONS

Security System

KFY FFATURFS

Long Endurance

No Passivation

- Smart Metering
- RFID and Tracking System
- Wireless Transmitting

- Smart Home Devices
- Military Devices

(Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult HCB.)



Primary Lithium Battery CP253025 3.0V [Li-MnO₂]




Physical characteristics	
Width	Max 31.0mm
Height	Max 26.0mm
Thickness	Max 2.7mm
Typical weight	2.5g
Li metal content	0.08g

MSDS as per request Diode (1N4007, 1N5819)

PTC (SRS175...)

Tag, wire, connector, etc. available



Dimensions in mm (GB1804-m)

WARNING:

- Do Not Short Circuit
- Do Not Recharge
- Do Not Puncture
- Do Not Crush
- Do Not Dismantle
- Do Not Incinerate
- Do Not Mix New and Used Batteries
- Do Not Heat Above 100°C


This information is generally descriptive only and is not intended to make or imply any representation, guarantee or warranty with respect to any cells and batteries . Cell and battery designs/specif -ications are subject to modi cation withour notice. Contact HCB for the latest information

HCB BATTERY CO., LTD


Add: 37 Tianyuan Street, Dongxihu District, Wuhan, Hubei, China

P.O.: 430040 Tel: +86(0)2783248452 Fax: +86(0)2783248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V1.0 2024 01]

1.Typical discharge profiles at 23±2°C (at mid-discharge)



2.Voltage plateau versus Current and Temperature (at discharge stable phase)



3.Storage characteristics

