

# Primary Lithium Battery CP952434

3.0V [Li-MnO<sub>2</sub>]

#### BENEFITS

- High Voltage Response, Stable During Most of the Lifetime of the Application
- Energy Density up to 830Wh/L
- Wide Operating Temperature Range (-40  $^\circ\!C$  ~+70  $^\circ\!C$  )
- Low Self-discharge Rate (less than 1% per year after 1 year of storage at +25  $^\circ\text{C}$  )

# - HCB 1604 CP952434 + 3.0V 1700mAh

## **References Data**

#### Electrical characteristics

Open circuit voltage (at 25°C)

### 3.10V 1700mAh

#### Nominal capacity

(At +25°C, battery discharged at continuous current 5mA until voltage reaches cut-o voltage 2.0V. The capacity can vary at di erent temperature, discharge current or cut-o voltage.)

#### Maximum continuous current

(At +25°C, 2.0V cut-o  $\,$  , battery discharged for minimum 50% of rated capacity.)

#### Maximum pulse discharge current

1000mA

600mA

(At +25°C, 2.0V cut-o , battery discharged for minimum 50% of rated capacity with max pulse for 3 seconds after 27 seconds break. Discharge capacity of the battery will change with the pulse characteristics and ambient temperature as well as storage situation. For more detail, please inquiry HCB.)

#### Storage (recommended)

(For more severe conditions, consult HCB) 75%RH

#### Operating temperature range

-40°C~+70°C

+30°C

(Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses, consult HCB.)

#### **KEY FEATURES**

- Optimized Battery Structure, Full Discharge Capacity
- Long Endurance
- No Passivation
- GB 8897.4-2008 IEC 60086.4:2014 and RoHS

#### MAIN APPLICATIONS

- Security System
- Smart Metering
- RFID and Tracking System
- Wireless Transmitting
- Smart Home Devices
- Military Devices

HCB BATTERY CO., LTD

Add: 37 Tianyuan Street, Dongxihu District, Wuhan, Hubei, China

P.O.: 430040 Tel: +86(0)27 83248452 Fax: +86(0)27 83248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V3.0 2023 05]


# Primary Lithium Battery CP952434



3.0V [Li-MnO<sub>2</sub>]

Physical characteristics	
Width	23.5±1.5mm
Height	34.0±1.0mm
Typical weight	13.7g
Li metal content	0.58g

MSDS as per request Diode (1N4007, 1N5819) PTC (SRS175...) Tag, wire, connector, etc. available



Dimensions in mm (GB1804-m)

### WARNING:


- Do Not Short Circuit
- Do Not Recharge
- Do Not Puncture
- Do Not Crush
- Do Not Dismantle
- Do Not Incinerate
- Do Not Mix New and Used Batteries
- Do Not Heat Above 100°C

This information is generally descriptive only and is not intended to make or imply any representation, guarantee or warranty with respect to any cells and batteries. Cell and battery designs/speci -cations are subject to modi cation withour notice. Contact HCB for the latest information


#### HCB BATTERY CO., LTD

Add: 37 Tianyuan Street, Dongxihu District, Wuhan, Hubei, China

P.O.: 430040 Tel: +86(0)27 83248452 Fax: +86(0)27 83248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V3.0 2023 05]



2. Voltage plateau versus Current and Temperature (at discharge stable phase)



3. Storage characteristics

