Primary Lithium Battery CR14250SC

3.0V [Li-MnO₂] 1/2AA-size bobbin cell

BENEFITS

- High Voltage Response, Stable During Most of the Lifetime of the Application
- Energy Density up to 830Wh/L
- Wide Operating Temperature Range (-40 °C ~+70 °C)
- Low Self-discharge Rate (less than 1% per year after 1 year of storage at +25 $^\circ\mathrm{C}$)

KEY FEATURES

- Optimized Battery Structure, Full Discharge Capacity
- Long Endurance
- No Passivation
- GB 8897.4-2008, IEC 60086.4:2014 and RoHS

MAIN APPLICATIONS

- Security System
- Smart Metering
- RFID and Tracking System
- Wireless Transmitting
- Smart Home Devices
- Military Devices

Reference Data

Electrical characteristics

Open circuit voltage (at 25°C)

Nominal capacity

(At +25°C, battery discharged at continuous current 1mA until voltage reaches cut-o voltage 2.0V. The capacity can vary at di erent temperature, discharge current or cut-o voltage.)

Maximum continuous current

(At +25°C, 2.0V cut-o $\,$, battery discharged for minimum 50% of rated capacity.)

Maximum pulse discharge current

(Maximum pulse discharge current is 30mA. Discharge capacity of the battery will change with the pulse characteristics and ambient temperature as well as storage situation. For more detail,please inquiry HCB.)

Storage (recommended)	+30°C
(For more severe conditions, consult HCB)	75%RH
Operating temperature range	-40°C~+70°C

(Consult HCB when using batteries at temperature exceeding -20°C~+60°C.)

HCB BATTERY CO., LTD

Add: 37 Tianyuan Street, Dongxihu District, Wuhan, Hubei, China

P.O.: 430040 Tel: +86(0)27 83248452 Fax: +86(0)27 83248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V3.1 2024 05]





15mA

30mA

3.10V

1050mAh


Primary Lithium Battery CR14250SC



3.0V [Li-MnO₂] 1/2AA-size bobbin cell

Physical characteristics	
Diameter	Max 14.5mm
Height	Max 26.0mm
Typical weight	10.0g
Li metal content	0.30g

MSDS as per request Diode (1N4007, 1N5819) PTC (SRS175...) Tag, wire, connector, etc. available



WARNING:

- Do Not Short Circuit
- Do Not RechargeDo Not Puncture
- Do Not Incinerate

Do Not Dismantle


- Do Not Mix New and Used Batteries
- Do Not Crush
- Do Not Heat Above 100°C

This information is generally descriptive only and is not intended to make or imply any representation, guarantee or warranty with respect to any cells and batteries . Cell and battery designs/specif -ications are subject to modi cation withour notice. Contact HCB for the latest information


HCB BATTERY CO., LTD

Add: 37 Tianyuan Street, Dongxihu District, Wuhan, Hubei, China

P.O.: 430040 Tel: +86(0)2783248452 Fax: +86(0)2783248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V3.1 2024 05]



2.Voltage plateau versus Current and Temperature` (at discharge stable phase)



3.Storage characteristics

